

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<p>(51) International Patent Classification <sup>6</sup> : <b>C25D 5/00, 5/02, 17/12</b></p>	<p><b>A1</b></p>	<p>(11) International Publication Number: <b>WO 95/20064</b> (43) International Publication Date: 27 July 1995 (27.07.95)</p>
<p>(21) International Application Number: PCT/US95/01141 (22) International Filing Date: 24 January 1995 (24.01.95) (30) Priority Data: 08/185,468 24 January 1994 (24.01.94) US (71)(72) Applicant and Inventor: BERG, N., Edward [US/US]; 43 Smith Road, Bedford, NH 03110 (US). (74) Agent: SOLOWAY, Norman, P.; Hayes, Soloway, Hennessey, Grossman &amp; Hage, P.C., 175 Canal Street, Manchester, NH 03101 (US).</p>		<p>(81) Designated States: CA, JP, KR, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).  <b>Published</b> <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i></p>
<p>(54) Title: <b>UNIFORM ELECTROPLATING OF PRINTED CIRCUIT BOARDS</b></p> <p>(57) Abstract</p> <p>A method and apparatus for the uniform electroplating of printed circuit boards is described. In one embodiment of the present invention, selected areas of the electroactive surface of the anode (15) or cathode electrode (26) are covered with a mask (18), whereby to establish substantially uniform electroplating ion transfer over the target areas of the target cathode (26).</p>		

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

1        UNIFORM ELECTROPLATING OF PRINTED CIRCUIT BOARDS

2

3        This invention relates to electroplating or electro-  
4 deposition of metal on a target. The invention has  
5 particular utility in connection with electro-deposition  
6 of metal onto printed circuit boards or panels and will be  
7 described in connection with such utility, although other  
8 utilities are contemplated.

9        Electroplating is an established process of producing  
10 a metallic coating on a surface. Such coatings may  
11 perform a protective function to prevent corrosion of the  
12 metal on which they are deposited, e.g., plating with zinc  
13 or tin (electro-galvanizing); or a decorative function,  
14 e.g., gold or silver plating; or both functions, e.g.,  
15 chromium plating.

16       The principal of electroplating is that the coating  
17 metal is deposited from an electrolyte, typically an  
18 aqueous acid or alkaline solution, onto a target substrate  
19 or panel. The latter forms the cathode (negative  
20 electrode) while a plate of the metal to be deposited  
21 serves as the anode (positive electrode). Alternatively,  
22 the anode may be made of an electrochemically inert (that  
23 is, not subject to decomposition during electroplating)  
24 metal and the plating metal may be deposited onto the  
25 cathode solely from the electrolytic solution.

26       Usually, the cathode is coated with an industry  
27 standard resist material to prevent plating of those areas  
28 of the cathode covered with the resist. After plating of  
29 the cathode, the resist pattern is removed, thereby  
30 leaving unplated the areas of the cathode that had been  
31 covered with the resist. As will be appreciated, such  
32 conventional resist patterns are incapable of solving the  
33 problems with which the present invention is concerned.

34       During a standard electroplating process, the  
35 periphery of the printed circuit board, i.e., the portions  
36 of the printed circuit board adjacent its outer edges,

-2-

1 tends to be at a higher current density than the center of  
2 the printed circuit board. Hence, metal deposits more  
3 rapidly adjacent the periphery of the printed circuit  
4 board than at the center. The result of this is that by  
5 the time the metal has deposited at the center of the  
6 circuit board to form a desired thickness, the metal  
7 deposited adjacent the periphery is at a thickness much  
8 greater than the thickness at the center. As a result,  
9 the width of depositing metal lines may grow laterally,  
10 and the resulting plated lines near the periphery may  
11 develop a cross sectional configuration resembling a  
12 mushroom.

13 In U.S. Patent No. 4,828,654, it is reported that by  
14 spacing the cathode a relatively large distance from the  
15 anode, and by making the effective size of the panel to be  
16 plated, i.e. the cathode, larger in size than the anode,  
17 there is more uniform distribution of the electroplating  
18 field. The more uniformly distributed field causes the  
19 metallic ions to be electrolytically deposited at a more  
20 uniform rate over the articles in the panel. This prior  
21 art arrangement reportedly avoids undesirable uneven  
22 plating build-up on the articles at those areas where  
23 there is a concentration of the electroplating field. It  
24 is also reported that field concentrations occur when the  
25 size of the article is smaller than the size of the anode,  
26 and results in the edges of the article experiencing a  
27 substantially greater build up of metallic ions than the  
28 center area of the article. Making the effective size of  
29 the cathode (the article to be plated) greater than the  
30 size of the anode and spacing the anode a relatively large  
31 distance from the cathode, operates to discourage the  
32 formation of areas of concentration in the electroplating  
33 field and encourages the ion transfer to become more  
34 uniform over the entire area of the cathode.

35 U.S. Patent No. 4,828,654 teaches an anode used in  
36 electroplating formed by a plurality of individual anode

-3-

1 segments which can be selectively energized to establish  
2 an effective anode size that relates to the size of the  
3 article to be electroplated, thereby establishing an  
4 electrical field of more uniform characteristics to  
5 transfer ions from the anode to the articles at a more  
6 uniform deposition rate over the whole surface of the  
7 article. By adjusting the effective size of the anode to  
8 correspond and relate to the size of the article, the non-  
9 uniform deposition rates associated with concentrated  
10 localized field reportedly are avoided, and the physical  
11 size of the electroplating apparatus can be reduced.

12 U.S. Patent No. 4,933,061 teaches an electroplating  
13 apparatus for electroplating a plurality of items. The  
14 patented apparatus includes a tank having a bottom wall  
15 and side walls, adapted to hold a predetermined quantity  
16 of electrolytic plating solution. A sparger system at the  
17 bottom of the tank directs the electrolytic plating  
18 solution in an upward direction. A cathode rack supports  
19 the items to be electroplated and extends intermediate to  
20 the anode plates and upwardly from the sparger system.  
21 Strategically placed openings in the anodes and an anode  
22 screen in conjunction with the sparger system reportedly  
23 act to reduce the plating thickness variance over the  
24 rack.

25 In U.S. Patent No. 5,017,275, there is disclosed an  
26 anode structure comprising a resilient anode sheet having  
27 an active anode surface, and a support sub-structure for  
28 the anode sheet. The anode sub-structure has a pre-  
29 determined configuration. By flexing the anode sheet onto  
30 the anode sub-structure, so that the anode sheet conforms  
31 to the configuration of the anode sub-structure, there  
32 reportedly is provided an adequate electrical junction for  
33 substantially uniform current distribution.

34 A collection of the known variables which affect the  
35 electroplating process have been set out in detail in the  
36 HANDBOOK OF PRINTED CIRCUIT MANUFACTURING by Raymond H.

-4-

1 Clark (1985). Therein it is reported that the factors  
2 which effect the electroplating process include:

- 3 1. plating pattern geography;
- 4 2. panel thickness and size of plated through holes;
- 5 3. panel borders;
- 6 4. plating rack;
- 7 5. bath chemistry, e.g., concentration of metals  
8 and acids, concentration of organic leveling and  
9 brightening agents, concentration of contaminants;
- 10 6. bath temperature;
- 11 7. anode-cathode spacing;
- 12 8. anode current density;
- 13 9. anode depletion;
- 14 10. plating bath agitation;
- 15 11. cathode agitation;
- 16 12. rectifier consideration; and
- 17 13. the skill and experience of the plater.

18 The present invention provides an improved  
19 electroplating system which overcomes the aforesaid and  
20 other problems of the prior art which have resulted in  
21 less than uniform electroplating and metallic deposition,  
22 and in so doing provides substantially uniform  
23 distribution of the deposited metal, from item to item in  
24 an electroplating process.

25 In accordance with the present invention, a system for  
26 electroplating comprises a receptacle for holding a bath  
27 of electroplating solution. An electrically conducting  
28 anode electrode is positioned within the receptacle in  
29 contact with the bath. In one preferred embodiment, the  
30 anode is covered at least in part with one or more  
31 electrically non-conductive masks which operate to direct  
32 the electric current as it travels through the  
33 electroplating solution to distribute over the cross-  
34 sectional surface area of a conductive substrate immersed  
35 in the electroplating receptacle at a location spaced  
36 apart from the anode to establish substantially uniform

-5-

1 electroplating ion transfer over the surface of the  
2 substrate. The mask or masks may be in direct contact  
3 with the anode, or in close proximity thereto. Completing  
4 the system are means for electrically energizing the anode  
5 and completing the circuit to the target/cathode.

6 The overall size of the anode, and the size and shape  
7 of the mask or masks, mask openings, number of openings,  
8 and location of openings in the non-conductive mask are  
9 all selected with reference to the size, target  
10 configuration and aspect ratio (anode-to-target) of the  
11 article to be electroplated. The distance separating the  
12 masked anode from the target panel substrate also is  
13 adjusted to promote uniform targeting of the  
14 electroplating current.

15 The present invention also provides a method of  
16 electroplating an article with a generally uniform  
17 thickness coating. In one preferred embodiment, this  
18 method comprises covering the anode electrode at least in  
19 part with one or more electrically non-conductive masks  
20 having a pattern of openings of predetermined  
21 configuration relative to the target cathode whereby to  
22 result in substantially uniform deposition over the target  
23 during electroplating.

24 Further features and advantages of the present  
25 invention will be apparent from the following detailed  
26 description of the invention taken in conjunction with the  
27 drawings, wherein like numerals depict like parts, and  
28 wherein:

29 Figure 1 is a perspective view of an electroplating  
30 apparatus embodying the present invention;

31 Figure 2 is a side view of portions of the  
32 electroplating system of Figure 1; and

33 Figure 3 is a view similar to 2, and illustrating an  
34 alternative form of electroplating system made in  
35 accordance with the subject invention;

-6-

1        Figure 4 is a side view of portions of another  
2 preferred embodiment of an apparatus embodying the present  
3 invention;

4        Figure 5 is a side view of portions of a variant of  
5 the embodiment of Figure 4;

6        Figure 6 is a side view of portions of a further  
7 variation of the embodiment of Figure 4; and

8        Figure 7 is a partial side-elevational view of an  
9 alternative anode construction for use in the embodiments  
10 of Figures 4-6.

11       Referring to Figures 1 and 2, one embodiment 10 of an  
12 electroplating system according to the present invention  
13 is illustrated. System 10 includes an outer housing 12  
14 which is preferably formed of an electrically insulating  
15 and corrosion-resistant material such as plastic. The  
16 housing 12 includes means in the form of a downward  
17 extending receptacle 14 for holding a bath of an  
18 electroplating solution 16. By way of example, for  
19 electroplating copper, bath 16 may comprise a copper  
20 sulfate solution commonly referred to as "acid copper".  
21 The plastic material of the housing 12 and receptacle 14  
22 resists the toxic and corrosive effects of the bath 16.

23       The electroplating system 10 includes an anode  
24 electrode 15 which preferably is covered at least in part  
25 with a non-conductive mask 18 (Figure 2), which will be  
26 described in detail below. Mask 18 may be coated directly  
27 on the electro-active surface of anode electrode 15 or may  
28 comprise a separate element which may be fixed to or  
29 suspended in close proximity to the electro-active surface  
30 of electrode 15. The anode electrode 15 and mask 18 are  
31 suspended from an upper support member 20 which is  
32 preferably formed of plastic to resist the corrosive  
33 effects of the bath 16 and to provide electrical  
34 insulation. The anode electrode 15 and mask 18 are held  
35 suspended from the support member 20 by fasteners such as  
36 non-corrosive titanium machine screw 22.



-7-

1       The article to be plated typically comprises a printed  
2 circuit board 26 which becomes the electrical cathode of  
3 the electroplating system during electroplating. The  
4 printed circuit board 26, which may be covered with an  
5 industry standard resist material (not shown), is  
6 suspended in the bath by a clamp 28 which includes a  
7 thumbscrew 30 or other similar fastening device for  
8 attaching and suspending or supporting the article to be  
9 electroplated in the bath. Clamp 28 in turn is  
10 mechanically connected to an electrically insulating  
11 support member 34. A handle 36 extends above the support  
12 member to allow the printed circuit board to be inserted  
13 into and removed from the bath 16 at the start and end of  
14 the electroplating process.

15       Completing the system are electrical conductors 29 and  
16 32 for electrically connecting the anode electrode 15 and  
17 cathode target 26 to a direct current or quasi direct  
18 current electrical energy source 38.

19       A feature and advantage of the present invention is  
20 the ability to substantially and uniformly electroplate  
21 the conductor paths, lands and holes of a target printed  
22 circuit board. Preferably, this is accomplished by  
23 covering selected areas of the electro-active surface of a  
24 solid anode 15 with a non-conductive mask 18 which directs  
25 the electric current through the electroplating solution  
26 so that the metal will be deposited onto the target  
27 cathode in a controlled (that is, in a substantially  
28 uniform) manner. The overall size of the anode, and the  
29 size and shape of the openings, number of openings, and  
30 location of the openings in the non-conductive mask are  
31 selected with reference to the size and geometry of the  
32 target article to be electroplated, with the result that  
33 field concentrations at any location on the target article  
34 are avoided, thereby achieving a relatively uniform layer  
35 of electroplated material.

36       Typically, the mask generally will have openings which

-8-

1 are substantially the negative of the target article.  
2 However, in order to compensate for uneven plating buildup  
3 on the target panel periphery, the mask openings  
4 corresponding to peripheral areas of the target board  
5 preferably should be made relatively smaller than  
6 corresponding deposition areas on edges of the target  
7 board, while the mask openings corresponding to center  
8 areas of the target board preferably should be made  
9 relatively larger than the corresponding deposition areas  
10 on center areas of the target board. Mask size and shape  
11 may be empirically determined using the above criteria.  
12 The mask may be applied directly to the anode electro-  
13 active surface, for example, by coating, or the mask may  
14 comprise a separate element which may be fixed directly to  
15 or held in close proximity to the anode electro-active  
16 surface, thereby allowing various selected exposed  
17 portions of the anode to serve as a source of field  
18 concentration for the electroplating process.

19 The distance between the masked anode and the target  
20 printed circuit board should be limited to a relatively  
21 short distance, typically 2 to 3.5 inches at normal  
22 plating potentials, so that bulk transfer through the  
23 electroplating bath does not defeat the masking effect.

24 Certain changes may be made in the above constructions  
25 without departing from the spirit and scope of the  
26 invention. For example, as shown in Figure 3, it also is  
27 possible to achieve uniform deposition by covering the  
28 cathode with one or more non-conductive apertured masks.  
29 In such case, the mask or masks should be spaced a short  
30 distance, e.g. 1.75 to 3 inches from the cathode.  
31 Locating the mask less than 1.75 inches or more than 3  
32 inches from the cathode is not advised and may not achieve  
33 uniform deposition.

34 Other modifications are also possible. For example,  
35 as shown in Figure 4, in another preferred embodiment 40  
36 of the present invention similar to that shown in Figures

1 1-2, the anode 15 is placed in direct contact with mask 18  
2 which is placed in direct contact with cathode 26.  
3 Embodiment 40 also includes electrolyte circulation means  
4 42 (shown in dashed lines) which permits controlled  
5 circulation or flow F of electrolyte fluid 16 in bath  
6 receptacle 14. Circulation means 42 comprises at least  
7 one conventional nozzle means 44 connected to a  
8 conventional filtered pump 46 which pumps fluid 16 from  
9 bath 14 through pipe means 48 (via opening 50 in  
10 receptacle 14) to nozzle 44, and thence, back into  
11 receptacle 14. Preferably, nozzle means 44 comprises a  
12 conventional shuttered aperture 52 for controllably  
13 adjusting direction and magnitude of fluid flow from  
14 nozzle 44. Advantageously, by appropriately adjusting  
15 direction and velocity of the flow of fluid in bath 14,  
16 the uniformity and speed of deposition of electroplating  
17 material upon cathode 26 may be increased.

18 Figure 5 shows a variation 60 of the embodiment 40 of  
19 Figure 4, in which variation 60 circulating means 42  
20 comprises a plurality of nozzle means 44A . . . 44J  
21 configured into two oppositely facing banks 62A, 62B of  
22 nozzles on opposite sides of board 26. In this embodiment  
23 60, the nozzles 44A . . . 44J are connected to a common  
24 combination pressure manifold and circulatory pump 46.  
25 Of course, each of the nozzles 44A . . . 44J or any number  
26 of them may be connected to independent pumps and/or  
27 pressure manifolds (not shown), without departing from the  
28 present invention. Additionally, although only two banks  
29 of five nozzles each are shown in Figure 5, it will be  
30 appreciated that the number and configuration of nozzles  
31 may be varied without departing from this embodiment 60 of  
32 the present invention.

33 Various other modifications are also possible without  
34 departing from the present invention. For example, the  
35 nozzles 44A . . . 44J of embodiment 60 of Figure 5 may  
36 comprise respective conventional shuttered-apertures.

-10-

1 Additionally, as shown in Figure 6, the embodiments shown  
2 in Figures 4 and 5 may comprise conventional controllable  
3 electromotive means 64A . . . L connected to circulation  
4 means 42 to permit the nozzles to move within bath 14.  
5 Preferably, electromotive means 64A . . . L are controlled  
6 via conventional programmable controller device 66 to move  
7 the nozzles according to a predetermined pattern to  
8 improve deposition of electroplating material upon cathode  
9 26 by providing appropriate flow F of electrolyte fluid in  
10 the bath.

11 Also alternatively, the embodiments shown in Figures  
12 4-6 may comprise an alternative anode 15A shown in Figure  
13 7. Anode 15A (which preferably is made of an  
14 electrochemically inert material) may be used by itself  
15 (i.e., without necessitating use of a mask) to accomplish  
16 substantially uniform electroplate ion transfer onto the  
17 target cathode. Preferably, anode 15A comprises a  
18 metallic, fine wire mesh grid 74 having a plurality of  
19 relatively small openings (representatively referred to by  
20 numeral 72). The dimensions of the openings 72 of grid  
21 anode 15A are empirically determined so as to permit  
22 substantially uniform electroplate ion transfer onto  
23 cathode 26. Preferably, when alternative anode 15A is  
24 substituted into the embodiments of Figures 4-6, the anode  
25 15A and cathode 26 are separated from each other by a  
26 distance much smaller than 2 to 3.5 inches; preferably,  
27 this distance is made such that the anode and cathode  
28 almost contact each other. Alternatively, anode 15A may  
29 be placed in direct contact with industry standard plating  
30 resist on cathode 26.

31 Additionally, the industry standard plating resist  
32 pattern usually placed on cathode 26 prior to the  
33 electroplating process may be adjusted using computer  
34 simulation techniques so as to aid the mask 18 and/or  
35 anode 15A in establishing uniform electroplate ion  
36 transfer according to the present invention.

-11-

1       Other modifications may also be possible. It is  
2 accordingly intended that all matter contained in the  
3 above description or shown in the accompanying drawings  
4 shall be interpreted as illustrative and not in a limiting  
5 sense.

-12-

CLAIMS

- 1  
2
- 3 1. In an apparatus for electroplating a target  
4 cathode, said apparatus including an anode electrode  
5 having an electroactive surface in contact with  
6 electrolytic fluid of an electroplating bath, the  
7 improvement which comprises at least one electrically non-  
8 conductive apertured mask in direct contact with and  
9 covering said cathode at least in part whereby to direct  
10 electric current through the electroplating solution in a  
11 controlled manner onto the target cathode, said anode  
12 being placed in direct contact with said mask (26) on said  
13 cathode, and means (46) for controllably circulating said  
14 fluid of said bath.
- 15 2. In an apparatus according to claim 1, the  
16 improvement characterized by one or more of the following  
17 features:
- 18 (a) said circulating means comprises at least  
19 one nozzle means (44) for directing flow of said  
20 circulating fluid in said bath;
- 21 (b) said cathode is interposed between banks of  
22 facing nozzle means (44A . . .) for directing flow of said  
23 circulating fluid in said bath;
- 24 (c) said circulating means comprises at least  
25 one nozzle means (44A . . .) having adjustable shutter  
26 means for changeably directing flow of said circulating  
27 fluid in said bath;
- 28 (d) said at least one mask (15A) comprises a  
29 plurality of openings (72) which are adjusted to establish  
30 substantially uniform electroplate ion transfer onto the  
31 target cathode;
- 32 (e) said cathode is interposed between two banks  
33 of oppositely facing nozzle means (44A . . .) having  
34 adjustable shutter means for changeably directing flow of  
35 said circulating fluid in said bath; and wherein said  
36 circulation means preferably comprises at least one nozzle

-13-

1 means and electromotive means (64A . . .) for controllably  
2 moving said nozzle means;  
3 (f) said circulation means comprises a plurality  
4 of nozzles connected to a combination pump (64) and  
5 manifold for circulating said fluid of said bath, and  
6 wherein at least one additional mask preferably is  
7 interposed between said anode and said at least one mask  
8 of said cathode, said circulation means preferably  
9 comprises controllable electromotive means (64A . . .) for  
10 controllably moving said nozzle means, and said nozzle  
11 means (44A . . .) preferably has shutter means for  
12 changeably directing flow of said circulating fluid in  
13 said bath; and

14 (g) said cathode comprises a conventional resist  
15 pattern disposed thereon, which pattern is adjusted to aid  
16 said at least one mask in establishing substantially  
17 uniform electroplate ion transfer to said cathode.

18 3. In an apparatus for electroplating a target  
19 cathode, said apparatus including an anode electrode  
20 having an electroactive surface in contact with  
21 electrolytic fluid of an electroplating bath, the  
22 improvement which comprises said anode being closely  
23 spaced from said cathode, said anode including a wire mesh  
24 (74) defining a plurality of openings (72) which are  
25 dimensioned to permit substantially uniform electroplate  
26 ion transfer onto said cathode, and means (46) for  
27 controllably circulating said fluid of said bath.

28 4. In an apparatus according to claim 3, the  
29 improvement characterized by one or more of the following  
30 features:

31 (a) said mesh (74) has a grid-like  
32 configuration;

33 (b) said circulating means comprises at least  
34 one nozzle means (44 . . .) and electromotive means for  
35 controllably moving said nozzle means;

-14-

1           (c) said circulating means preferably further  
2 comprises a programmable controller device (46) for  
3 permitting predetermined motion of said nozzle means; and  
4           (d) said cathode comprises a conventional resist  
5 pattern disposed thereon, which pattern is adjusted to aid  
6 in establishing substantially uniform electroplate ion  
7 transfer to said cathode.

8       5. In a process for electroplating a target cathode  
9 using an apparatus including an anode electrode having an  
10 electroactive surface in contact with electrolytic fluid  
11 of an electroplating bath, the improvement which comprises  
12 placing at least one electrically non-conductive apertured  
13 mask in direct contact with and covering said cathode at  
14 least in part whereby to direct electric current through  
15 the electroplating solution in a controlled manner onto  
16 the cathode, placing said anode in direct contact with  
17 said mask on said cathode, and controllably circulating  
18 said fluid of said bath so as to permit substantially  
19 uniform electroplating ion transfer onto said cathode.

20       6. In a process for electroplating according to  
21 claim 5, the improvement characterized by one or more of  
22 the following features:

23           (a) said fluid circulation is accomplished, at  
24 least partially, by directing flow of said fluid through  
25 at least one nozzle means, preferably by moving said  
26 nozzle means according to a predetermined pattern;

27           (b) said fluid circulation is accomplished, at  
28 least partially, by directing flow of said fluid through  
29 at a plurality of nozzle means, preferably by moving said  
30 nozzle means according to a predetermined pattern.

31       7. In a process for electroplating a target cathode  
32 using an apparatus including an anode electrode having an  
33 electroactive surface in contact with electrolytic fluid  
34 of an electroplating bath, the improvement which comprises  
35 forming said anode so as to include a wire mesh defining a  
36 plurality of openings which are dimensioned to permit



-15-

1 substantially uniform electroplating ion transfer onto  
2 said cathode, placing said anode in close proximity to  
3 said cathode, and controllably circulating said fluid in  
4 said bath.

5 8. In a process according to claim 7, the  
6 improvement characterized by one or more of the following  
7 features:




8 (a) said mesh has a grid-like configuration;

9 (b) said circulation of said fluid is  
10 accomplished, at least in part, by directing said fluid  
11 through at least one nozzle means, preferably by moving  
12 said nozzle means in said bath, preferably wherein said  
13 movement of said nozzle means is predetermined;


14 (c) further comprising adjusting formation of a  
15 conventional resist pattern disposed upon said cathode so  
16 as to aid said at least one mask in establishing  
17 substantially uniform electroplate ion transfer to said  
18 cathode; and

19 (d) further comprising adjusting formation of a  
20 conventional resist pattern disposed upon said cathode so  
21 as to aid said at least one mask in establishing  
22 substantially uniform electroplate ion transfer to said  
23 cathode.

1 / 5



2 / 5



**FIG. 4**

**SUBSTITUTE SHEET (RULE 26)**

3 / 5




FIG. 5

SUBSTITUTE SHEET (RULE 26)



5 / 5




FIG. 7

## INTERNATIONAL SEARCH REPORT

 International application No.  
 PCT/US95/01141

## A. CLASSIFICATION OF SUBJECT MATTER

IPC(6) : C25D 5/00, 5/02, 17/12

US CL : 204/224R; 205/96

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

U.S. : 204/224R, 237; 205/96, 118, 125, 126, 135

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

APS

circuit board or printed circuit, mesh anode, current distribution

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	US, A, 3,008,892 (OWEN) 14 November 1961, column 2, lines 1-19, figures 1-3.	1, 2, 5, 6
Y	US, A, 3,503,856 (BLACKMORE) 31 March 1970, column 2, lines 59-64, figures 1 and 2.	1-8
Y	US, A, 3,835,017 (MENTONE ET AL) 10 September 1974, column 3, lines 2-8, figure 2.	1-8
A	US, A, 3,962,047 (WAGNER) 08 June 1976.	1-8
X	US, A, 4,220,506 (SKURKISS ET AL) 02 September 1980, column 3, lines 20-26, figures 1 and 3.	3, 4, 7, 8
X	US, A, 4,394,241 (SCANLON) 19 July 1983, column 4, lines 8-60, figures 3 and 4.	3, 4, 7, 8

☒ Further documents are listed in the continuation of Box C.
 ☐ See patent family annex.

* Special categories of cited documents:	*T	later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
*A* document defining the general state of the art which is not considered to be of particular relevance	*X*	document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
*E* earlier document published on or after the international filing date	*Y*	document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
*L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	*Z*	document member of the same patent family
*O* document referring to an oral disclosure, use, exhibition or other means		
*P* document published prior to the international filing date but later than the priority date claimed		

Date of the actual completion of the international search

12 JUNE 1995

Date of mailing of the international search report

05 JUL 1995

 Name and mailing address of the ISA/US  
 Commissioner of Patents and Trademarks  
 Box PCT  
 Washington, D.C. 20231

Facsimile No. (703) 305-3230

Authorized Officer

JOHN NIEBLING

Telephone No. (703) 308-3325